



www.nerligruppen.com

AWNINGS & PERGOLITE
Fabrics Collection

NATUREL
ORC 7133



PIERRE
ORC 6196



PERLE
ORC 7972



GRIS
ORC 6088



TITANE
PIQUÉ
ORC U408



ACIER
PIQUÉ
ORC U406



BORDEAUX
ORC 8206




DUNE
ORC 0681



SOURIS
ORC 8396



PLATINE
PIQUÉ
ORC U407



FLANELLE
ORC U104



BASALTE
CHINÉ
ORC U095



ARDOISE
ORC 8203



NOIR
ORC 6028



CARBONE
ORC U171




CHARCOAL
TWEED
ORC 7330





Comosition	Acrylic 100%, solution dyed
Finishing	Cleangard special dirt-resistant and awning water repellent treatment
 Weight (g/m2)	290 g/m2
 Width	120 cm
Tensile strength	140 daN Wrap / 90 daN Weft
 Tear strength	4 daN Wrap / 2,3 daN Weft
 Water repellency	> 370 mm
 Colour fastness weather condition	4-5 / 5

0079




407/151




407/324



407/94




4215/97








873/926



94/97








Comosition	100% acrylic fibre solution dyed "outdoor"
Finishing	water/oil repellent, resistant to mould, stains, salt and U.V. fading
 Weight (g/m2)	300 g/m2
 Width	120 cm
Tensile strength	160 daN Wrap / 86 daN Weft
 Tear strength	3,1 daN Wrap / 1,4 daN Weft
 Water repellency	> 300 mm
 Colour fastness weather condition	7-8

338-655



338-665



Comosition	100% acrylic
Finishing	TEXgard finish, water and soil repellent
 Weight (g/m2)	290 g/m2
 Width	120 cm
Tensile strength	160 daN Wrap / 120 daN Weft
 Tear strength	4,1 daN Wrap / 4,1 daN Weft
 Water repellency	460 mm
 Colour fastness weather condition	min. 7

G348
QUADRA



G674
TEXTURES



G077
TEXTURES








G053
TEXTURES



G413
QUADRA



Comosition	100% acrylic
Finishing	Acrylic with high water reppellency, Duraclean
 Weight (g/m2)	290 g/m2
 Width	120 cm
Tensile strength	140 DaN Wrap / 90 DaN Weft
 Tear strength	3,5 daN Wrap / 2,5 daN Weft
 Water repellency	350 mm
 Colour fastness weather condition	min. 7

